

Privacy Films

Parameter	MATTE WHITE	MATTE GREY	MATTE BRONZE
Thickness	2 Mil	2 Mil	2 Mil
Visible Light Transmittance	77 %	36 %	35 %
Visible Light Reflectance	9 %	7 %	7 %
Solar Energy Transmittance	61 %	55 %	56 %
Solar Energy Reflectance	8 %	7 %	6 %
Solar Energy Absorbance	31 %	38 %	38 %
Ultra Violet Transmittance	< 2 %	< 2 %	< 2 %
Glare Reduction	15 %	60 %	61 %
Shading Coefficient	0.81	0.78	0.77
Emissivity	0.85	0.86	0.86
U Factor (BTU / Hr / Sq. ft.)	1.09	1.14	1.14
Total Solar Energy Rejection	30 %	34 %	33 %